

Please type a plus sign (+) inside this box → ☐

PTO/SB/05 (2/98)
Approved for use through 09/30/00. OMB 0651-0032
Patent and Trademark Office: U.S. DEPARTMENT OF COMMERCE
Under the Paperwork Reduction Act of 1995, no persons are required to respond to a collection of information unless it displays a valid OMB control number.

UTILITY PATENT APPLICATION TRANSMITTAL

(Only for new nonprovisional applications under 37 CFR 1.53(b))

Attorney Docket No. 03364.P010
First Inventor or Application Identifier Wan-uk Choi
Title ACTIVE NEGATIVE MATERIAL FOR LITHIUM SECONDARY BATTERY, METHOD OF PREPARING THE SAME AND LITHIUM SECONDARY BATTERY USING THE SAME
Express Mail Label No. EM560887808US

APPLICATION ELEMENTS

See MPEP chapter 600 concerning utility patent application contents

ADDRESS TO:

Assistant Commissioner for Patents
Box Patent Application
Washington, DC 20231

1. ☒ Fee Transmittal Form
(Submit an original, and a duplicate for fee processing)
2. ☒ Specification *Total Pages* 15
(preferred arrangement set forth below)
- Descriptive title of the Invention
 - Cross References to Related Applications
 - Statement Regarding Fed sponsored R & D
 - Reference to Microfiche Appendix
 - Background of the Invention
 - Brief Summary of the Invention
 - Brief Description of the Drawings (if filed)
 - Detailed Description
 - Claim(s)
 - Abstract of the Disclosure
3. ☒ Drawing(s) (35 CFR 113) *Total Sheets* 2
4. ☐ Oath or Declaration *Total Pages* 3
- a. ☒ Newly executed (original copy)
- b. ☐ Copy from a prior application (37 CFR 1.63(d))
(for continuation this is not required)
[Note Box 5 below]
- i. ☐ DELETION OF INVENTOR(S)
Signed statement attached deleting inventor(s) named in the prior application, see 37 CFR 1.63(d)(2) and 1.33(b).

5. ☐ Microfiche Computer Program (Appendix)
6. ☐ Nucleotide and/or Amino Acid Sequence Submission (if applicable, all necessary)
- a. ☐ Computer Readable Copy
- b. ☐ Paper Copy (identical to computer copy)
- c. ☐ Statement verifying identity of above copies

ACCOMPANYING APPLICATION PARTS

7. ☒ Assignment Papers (cover sheet & document(s))
8. ☐ 37 CFR 3.73(b) Statement ☐ Power of Attorney
(when there is an assignee)
9. ☐ English Translation Document (if applicable)
10. ☐ Information Disclosure Statement (IDS)/PTO - 1449 ☐ Copies of IDS Citations
11. ☐ Preliminary Amendment
12. ☒ Return Receipt Postcard (MPEP 503)
(Should be specifically itemized)
13. ☐ *Small Entity ☐ Statement filed in prior application, Statement(s) ☐ Status still proper and desired
14. ☐ Certified Copy of Priority Document(s)
(if foreign priority is claimed)
15. ☒ Other: request for priority; certified copy of korean patent appln. #1998-7854

16. If a **CONTINUING APPLICATION**, check appropriate box, and supply the requisite information below and in a preliminary amendment:

☐ Continuation ☐ Divisional ☐ Continuation-in-part (CIP) of prior application No: _____/_____

Prior application Information: Examiner _____ Group/Art Unit: _____

For **CONTINUATION** or **DIVISIONAL APPS** only: The entire disclosure of the prior application, from which an oath or declaration is supplied under Box 4b, is considered a part of the disclosure of the accompanying continuation or divisional application and is hereby incorporated by reference. The incorporation can only be relied upon when a portion has been inadvertently omitted from the submitted application parts.

17. CORRESPONDENCE ADDRESS

☐ Customer Number of Bar Code Label

(Insert Customer No. or Attach bare code label here)

or ☒ Correspondence address below

Name

BLAKELY, SOKOLOFF, TAYLOR & ZAFMAN LLP

Address

12400 Wilshire Boulevard, Seventh Floor

City

Los Angeles

State

California

Zip Code

90025

Country

U.S.A.

Telephone

(310) 207-3800

Fax

(310) 820-5988

Name (Print/Type)

Eric S. Hyman, Reg. No. 30,139

Signature

Eric S. Hyman

Date

3/10/99

Burden Hour Statement: This form is estimated to take 0.2 hours to complete. Time will vary depending upon the needs of the individual case. Any comments on the amount of time you are required to complete this form should be sent to the Chief Information Officer, Patent and Trademark Office, Washington, DC 20231. DO NOT SEND FEES OR COMPLETED FORMS TO THIS ADDRESS. SEND TO: Assistant Commissioner for Patents, Box Patent Application, Washington, DC 20231.

**ACTIVE NEGATIVE MATERIAL FOR LITHIUM SECONDARY BATTERY,
METHOD OF PREPARING THE SAME AND
LITHIUM SECONDARY BATTERY USING THE SAME**

CROSS-REFERENCES TO RELATED APPLICATIONS

This application is based on application No. 98-7854 filed in the Korean Industrial Property Office on March 10, 1998, the content of which is incorporated hereinto by reference.

BACKGROUND OF THE INVENTION

(a) Field of the Invention

The present invention relates to and an active negative material for lithium secondary battery, a method of preparing the same and a lithium secondary battery using the same, and more particularly, to an active negative material useful for fabricating a lithium secondary battery having a high capacity.

(b) Description of the Related Art

In recent years, the development of miniaturized portable electronics provokes needs for a secondary battery having a high capacity as well as a light weight. From the viewpoint of the capacity improvement per unit weight, the lithium secondary battery is preferably adopted because lithium has a high standard potential as well as a low electrochemical equivalent weight.

Fig. 1 is a schematic cross sectional view showing the general structure of the coin-typed lithium secondary battery. As shown in Fig. 1, the lithium secondary battery includes a positive electrode plate 40 having a collector 1

made of nickel and an active material layer 10 coated on the collector 1, a negative electrode plate 45 having a collector 1' made of copper and an active material layer 30 coated on the collector 1', and a separator 25 interposed between the positive and negative electrode plate 40 and 45. The positive and negative electrode plates 40 and 45 essentially form an electrode plate assembly together with the separator 25. The electrode plate assembly is inserted into an opening portion of a battery case 5 internally surrounded with a gasket 20 while receiving an electrolyte 15 therein. The opening portion of the battery case 5 is covered by a cap 35.

Fig. 2 is a schematic cross sectional view showing the general structure of the cylindrical-typed lithium secondary battery. As shown in Fig. 2, the lithium secondary battery includes positive electrodes 50, negative electrodes 55 stacked in order and separated by a separator 60. The layered structure is wound a number of times in a spiral form to obtain an electrode winding body. The electrode winding body is inserted into a battery can 90 including nickel plated steel insulating plates 80, 85 respectively inserted into the top and bottom of the battery can 90. For the purpose of collecting electricity of the negative electrode, one end of a nickel negative lead 75 is pressure-connected to the negative electrode, and the other end thereof is welded to the battery can 90. In addition, in order to collect electricity of the positive electrode, one end of an aluminum positive electrode lead 70 is attached to positive electrode 50, and the other end is welded to battery cover 100 having current interrupting mechanism 105.

Lithium-containing transitional metal oxide such as LiCoO_2 , LiNO_2 ,

LiMn₂O₄ and LiNi_xCo_{1-x}O_y are preferably selected for the positive electrode active materials in conjunction with a polyethylene-based porous film for the separator.

As for the negative electrode active materials, lithium metal is attractive because it has a light weight and high capacity per unit weight to thereby output high voltage in the battery use. However, the use of lithium metal for the negative electrode material reveals serious defects in a cycle life and stability of the battery because the lithium metal is highly reactive with the electrolytic solvent and easily forms needle dendrites during cycling, causing destruction of the separator and a short circuit. In order to avoid the defects, lithium alloys are employed as the negative electrode active material instead of the lithium metal but yet reveals similar problems.

Alternatively, carbon materials, which can reversibly accept and donate significant amounts of lithium without affecting their mechanical and electrical properties, are proposed for the negative electrode active material.

The carbon materials adapted for use in a battery are generally spherical type carbon materials and fiber type carbon materials. A method for preparing the spherical type carbon material is disclosed in Japanese Patent No. Hei 1-27968. In the method, a coal tar pitch is heat-treated and centrifuged to thereby produce small spherical particles having an optical anisotropy (referred to hereinafter more simply as mesophase particles). Alternatively, a coal tar pitch is centrifuged to obtain supernatant and the supernatant is heat-treated, obtaining mesocarbon microbeads.

However, the aforementioned techniques are not economical and the

manufacturing process is complicate because the centrifugation step should performed for obtaining mesophase particles. Furthermore, mesophase particles is only used for preparing spherical carbon materials, the total yield is low.

SUMMARY OF THE INVENTION

It is an object of the present invention to provide a negative active material for useful for fabricating a lithium secondary battery having a high capacity.

It is another object of the present invention to provide a method of preparing the negative active material with simple manufacturing process and high yield.

It is another object of the present invention to provide a lithium secondary battery using the negative active material.

In order to achieve this object and others, the present invention provides a negative active material including a graphite-like carbon material having an intensity ratio $I(110)/I(002)$ of an X-ray diffraction peak intensity $I(002)$ at a (002) plane to an X-ray diffraction peak intensity $I(110)$ at a (110) plane of less than 0.2. The negative active material is prepared by dissolving a coal tar pitch or a petroleum pitch in an organic solvent to remove insoluble components therefrom, heat-treating the pitch at a temperature in the range of 400 to 450 °C for four hours or more to thereby produce at least 50 weight percent of mesophase particles based on the pitch, coking the pitch including the mesophase particles, carbonizing the coked pitch, pulverizing the carbonized pitch and graphitizing the pulverized pitch.

The lithium secondary battery includes a negative electrode having the negative active material, a positive electrode having a lithium containing material that can reversibly intercalate and de-intercalate lithium ion and a non-aqueous electrolyte.

BRIEF DESCRIPTION OF THE DRAWINGS

A more complete appreciation of the invention, and many of the attendant advantages thereof, will be readily apparent as the same becomes better understood by reference to the following detailed description when considered in conjunction with the accompanying drawings:

FIG. 1 is a schematic diagram of a 2016 typed coin cell; and

FIG. 2 is a schematic diagram of a 18650 typed cylindrical cell.

DETAILED DESCRIPTION OF THE INVENTION

The negative active material for the lithium secondary battery according to the present invention includes a graphite-like carbon material which has an intensity ratio $I(110)/I(002)$ of an X-ray diffraction peak intensity $I(002)$ at a (002) plane to an X-ray diffraction peak intensity $I(110)$ at a (110) plane of less than 0.2.

The graphite-like carbon material more preferably has an intensity ratio $I(110)/I(002)$ of less than 0.04. That is, the lower the intensity ratio of the intensity at the (110) plane which reveal crystallinity during X-ray diffraction analysis, the higher the capacity of the graphite-like carbon material.

The negative active material is prepared by the following method. A coar tar pitch or a petroleum pitch is dissolved in an organic solvent to remove insoluble components therefrom. The organic solvent may be tetrahydrofuran,

quinoline, benzene or toluene. The pitch is heat-treated at a temperature in the range of 400 to 450 °C for 4 hours or more under an inert atmosphere such as nitrogen or argon to thereby produce at least 50 weight percent of mesophase particles based on the pitch. The mesophase particles contained in the pitch may present in the amount of 50 to 98 weight percent. The pitch including the 50 to 98 weight percent of mesophase particles is used for preparing negative active material, a battery having a high capacity can be produced.

The pitch including the mesophase particles is coked. The coking step is preferably performed at a rising temperature up to 600 °C under an inert atmosphere. Thereafter, the coked pitch is carbonized at a temperature in the range of 1,000 to 1,300 °C. The carbonizing step is to remove components such as H, N and O from the coked material. The components are not well removed at temperatures lower than 1,000 °C. On the other hand, when the carbonizing step is performed at temperature exceeding 1,300 °C, a fine structure is significantly developed, causing reduction in the charge and discharge capacity.

The carbonized pitch is pulverized to thereby produce no particular shape particles. The amorphous particles are graphitized at a temperature in the range of 2,500 to 3,000 °C. The graphitizing step is to arrange the fine structure of the carbonized material. When the graphitizing step is performed at temperatures below 2,500 °C, the crystalline structure is not well developed and amorphous portions may be present. On the other hand, when the graphitizing step is performed at temperatures exceeding 3,000 °C, the value of

I(110)/I(002) greatly increases and the charge and discharge efficiency is undesirably low. If the value of I(110)/I(002) exceeds 0.2, is more than, charge and discharge capacity decrease.

The present carbon material for used in the lithium secondary battery includes the mesophase particles in the optimum content. In the present invention, the optimum content is controlled by determining the electrochemical characteristics of the carbon material, while the mesophase particles content is changed.

Conventionally, as the mesophase particles, spherical or fibrous mesophase particles are only used for preparing a negative active material. Due to this, the separation of spherical or fibrous mesophase particles should be performed, causing the complication of negative active material manufacturing process. Furthermore, as the no spherical or no fibrous mesophase particles wastes, the total yield is low. On the hand, in the present invention, the mesophase particles having no particular shape is used in the present invention without separating spherical mesophase particles or fibrous mesophase particles. Therefore, a negative active material having a high capacity can be produced with a high yield.

In the present invention, the graphite-like carbon material having a high capacity is prepared by comparing an integral intensity I(002) of the X-ray diffraction peak at the (002) plane with an integral intensity I(110) of the X-ray diffraction peak at the prismatic plane (110). That is, main point of the present invention is posed on the twist of carbon atoms in an unit lattice of the crystalline structure, rather than on the contributing effect to the electric capacity

by separating the crystalline portion and the amorphous portion. Furthermore, when the value of $I(110)/I(002)$ is low, the identical effect can be obtained irrespective of crystallinity. The graphite-like carbon material for use in the present invention has a crystal size in the direction of the c axis (L_c) of 10-100 nm and in the direction of the a axis (L_a) of 20- 200 nm, the intensity ratio $I(110)/I(002)$ of an X-ray diffraction peak intensity $I(002)$ at a (002) plane to an X-ray diffraction peak intensity $I(110)$ at a (110) plane of 0.012 to 0.20, and a specific surface of 3-20 m^2/g .

The fine structure of the synthesized carbon material is changed in accordance with the preparing conditions and reveals difference to a natural graphite. The experimental tests exhibited that the lower the intensity ratio of the (002) plane to the (110) plane which reveal a crystallinity during X-ray diffraction analysis, the higher the capacity of the graphite-like carbon material. Therefore, a lithium secondary battery having a high capacity can be fabricated with a graphitic-like carbon material having a low intensity ratio of the (002) plane to the (110) plane for the negative electrode active material.

The present invention will be now described with reference to Examples and drawings.

Example 1

A coar tar pitch was dissolved in tetrahydrofuran and insoluble components were removed therefrom. The residual components were heat-treated at 430 °C for four hours under a gaseous nitrogen atmosphere to thereby produce 50 weight percent of mesophase particles based on the pitch. Thereafter, the resulting pitch including mesophase particles were heated at a

rising temperature up to 600 °C under a gaseous nitrogen atmosphere to thereby coke them. The coked pitch was then carbonized at 1000 °C. Next, the carbonized pitch was pulverized to thereby obtain a pulverized pitch having no particular shape. The pulverized pitch having no particular shape was graphitized at 2800 °C for 30 minutes under an inert atmosphere of gaseous nitrogen/argon atmosphere. As a result, a carbon material having a graphite structure was prepared.

Example 2

A carbon material was prepared by the same procedure in Example 1 except that the tetrahydrofuran-insoluble components removed pitch was heat-treated at 430 °C for 8 hours to thereby produce 70 weight percent of mesophase particles based on the pitch.

Example 3

A carbon material was prepared by the same procedure in Example 1 except that the tetrahydrofuran-insoluble components removed pitch was heat-treated at 430 °C for 15 hours to thereby produce 98 weight percent of mesophase particles based on the pitch.

Each of the graphite-like carbon materials according to the Examples 1 to 3 of the present invention was mixed with a solution of polyvinylene fluoride in a N-methyl pyrrolidone solvent to be thereby made into a slurry. Then, the slurry was coated on a collector made of copper foil to thereby form a negative electrode plate. Next, a lithium secondary cell was as shown in Fig. 1 prepared using the negative electrode plate together with a current electrode

made of lithium metal foil and an electrolyte of LiPF_6 in an organic solvent. The capacity and discharge efficiency (discharge capacity/ charge capacity) of each cell were measured and the results are presented in Table 1.

For comparison, a lithium secondary cell was prepared by the above method with mesocarbon microbeads (Japan, Osaka Gas). The capacity and discharge efficiency of the compared cell was also measured and the results are presented in Table 1.

Table 1

	Capacity [mAh/g]	Efficiency	I(110)/ I(002)
Example 1	290	88	0.016
Example 2	300	83	0.012
Example 3	314	92	0.015
Compared cell	280	85	0.20

For reference, a cylindrical cell as shown in Fig.2 was manufactured by using a negative electrode plate including the carbon material obtained by the Example 3 coated on a current collector made of copper foil and a positive electrode plate including LiCoO_2 coated on a collector made of the nickel foil. The capacity of the cylindrical cell was measured and the results are 1600 mAh.

As described above, in the present invention, the each of carbon materials having different mesophase particles content and is used for a lithium secondary battery, the lithium secondary battery having a high capacity can be prepared. Furthermore, the present invention can produce carbon material with a simple manufacturing process and a high yield.

While the present invention has been described in detail with reference to the preferred embodiments, those skilled in the art will appreciate that various modifications and substitutions can be made thereto without departing from the spirit and scope of the present invention as set forth in the appended claims.

WHAT IS CLAIMED IS:

1. A negative active material for a lithium secondary battery, comprising a graphite-like carbon material having an intensity ratio $I(110)/I(002)$ of an X-ray diffraction peak intensity $I(002)$ at a (002) plane to an X-ray diffraction peak intensity $I(110)$ at a (110) plane of less than 0.2, the negative active material prepared by

dissolving a coar tar pitch or a petroleum pitch in an organic solvent to remove insoluble components therefrom;

heat-treating the pitch at a temperature in the range of 400 to 450 °C for 4 hours or more under an inert atmosphere to thereby produce at least 50 weight percent of mesophase particles based on the pitch;

coking the pitch including mesophase particles;

carbonizing the coked pitch;

pulverizing the carbonized pitch; and

graphitizing the pulverized pitch.

2. The negative active material of claim 1 wherein the graphite-like carbon material has an intensity ratio $I(110)/I(002)$ of less than 0.04.

3. A lithium secondary battery comprising:

a negative electrode comprising a negative active material;

a positive electrode comprising a lithium containing material that can reversibly intercalate and de-intercalate lithium ion; and

a non-aqueous electrolyte;

the negative active material comprising a graphite-like carbon material having an intensity ratio $I(110)/I(002)$ of an X-ray diffraction peak intensity $I(002)$

at a (002) plane to an X-ray diffraction peak intensity $I(110)$ at a (110) plane of less than 0.2 and the negative active material prepared by

dissolving a coar tar pitch or a petroleum pitch in an organic solvent to remove insoluble components therefrom;

5 heat-treating the pitch at a temperature in the range of 400 to 450 °C for 4 hours or more under an inert atmosphere to thereby produce at least 50 weight percent of mesophase particles based on the pitch;

coking the pitch including mesophase particles;

carbonizing the coked pitch;

10 pulverizing the carbonized pitch; and

graphitizing the pulverized pitch.

4. The lithium secondary battery of claim 3 wherein the graphite-like carbon material has an intensity ratio $I(110)/I(002)$ of less than 0.04.

15 5. A method of preparing a negative active material for a lithium secondary battery, comprising the steps of:

dissolving a coar tar pitch or a petroleum pitch in an organic solvent to remove insoluble components therefrom;

20 heat-treating the pitch at a temperature in the range of 400 to 450 °C for 4 hours or more under an inert atmosphere to thereby produce at least 50 weight percent of mesophase particles based on the pitch;

coking the pitch including mesophase particles;

carbonizing the coked pitch;

pulverizing the carbonized pitch; and

graphitizing the pulverized pitch.

6. The method of claim 5 wherein the inert atmosphere is a gaseous nitrogen or argon atmosphere.

7. The method of claim 5 wherein the mesophase particles are produced by 50 to 98 weight percent based on the pitch.

5 8. The method of claim 5 wherein the coking step is performed at a rising temperature up to 600 °C under an inert atmosphere.

ABSTRACT OF THE DISCLOSURE

A negative active material for a lithium secondary battery includes a graphite-like carbon material having an intensity ratio $I(110)/I(002)$ of an X-ray diffraction peak intensity $I(002)$ at a (002) plane to an X-ray diffraction peak intensity $I(110)$ at a (110) plane of less than 0.2. The negative active material prepared by dissolving a coal tar pitch or a petroleum pitch in an organic solvent to remove insoluble components therefrom, heat-treating the pitch at a temperature in the range of 400 to 450 °C for 4 hours or more under an inert atmosphere to thereby produce at least 50 weight percent of mesophase particles based on the pitch, coking the pitch including mesophase particles, carbonizing the coked pitch, pulverizing the carbonized pitch; and graphitizing the pulverized pitch.

FIG. 1





FIG. 2



(Application Serial No.)	(Filing Date)	(Status -- patented, pending, abandoned)
(Application Serial No.)	(Filing Date)	(Status -- patented, pending, abandoned)
(Application Serial No.)	(Filing Date)	(Status -- patented, pending, abandoned)

I hereby appoint BLAKELY, SOKOLOFF, TAYLOR & ZAFMAN LLP, a firm including: Farzad E. Amini, Reg. No. 42,261; Aloysius T. C. AuYeung, Reg. No. 35,432; William Thomas Babbitt, Reg. No. 39,591; Carol F. Barry, 41,600; Jordan Michael Becker, Reg. No. 39,602; Bradley J. Berezna, Reg. No. 33,474; Michael A. Bernadicou, Reg. No. 35,934; Roger W. Blakely, Jr., Reg. No. 25,831; Gregory D. Caldwell, Reg. No. 39,926; Kent M. Chen, Reg. No. 39,630; Lawrence M. Cho, Reg. No. 39,942; Yong S. Choi, Reg. No. 43,324; Thomas M. Coester, Reg. No. 39,637; Roland B. Cortes, Reg. No. 39,152; Barbara Bokanov Courtney, Reg. No. P42,442; William Donald Davis, Reg. No. 38,428; Michael Anthony DeSanctis, Reg. No. 39,957; Daniel M. De Vos, Reg. No. 37,813; Tarek N. Fahmi, Reg. No. P41,402; James Y. Go, Reg. No. 40,621; Richard Leon Gregory, Jr., P42,607; Dinu Gruia, Reg. No. 42,996; David R. Halvorson, Reg. No. 33,395; Thomas A. Hassing, Reg. No. 36,159; James A. Henry, Reg. No. 41,064; Phuong-Quan Hoang, 41,839; Willmore F. Holbrow III, Reg. No. P41,845; George W. Hoover II, Reg. No. 32,992; Eric S. Hyman, Reg. No. 30,139; Dag H. Johansen, Reg. No. 36,172; William W. Kidd, Reg. No. 31,772; Tim L. Kitchen, Reg. No. P41,900; Michael J. Mallie, Reg. No. 36,591; Paul A. Mendonsa P42,879; Darren J. Milliken, P42,004; Thinh V. Nguyen, Reg. No. 42,034; Kimberley G. Nobles, Reg. No. 38,255; Michael A. Proksch P43,021; Babak Redjaian, Reg. No. 42,096; James H. Salter, Reg. No. 35,668; William W. Schaal, Reg. No. 39,018; James C. Scheller, Reg. No. 31,195; Anand Sethuraman, Reg. No. 43,351; Charles E. Shemwell, Reg. No. 40,171; Maria McCormack Sobrino, Reg. No. 31,639; Stanley W. Sokoloff, Reg. No. 25,128; Allan T. Sponseller, Reg. No. 38,318; Geoffrey T. Staniford, P43,151; Judith A. Szepesi, Reg. No. 39,393; Vincent P. Tassinari, Reg. No. 42,179; Edwin H. Taylor, Reg. No. 25,129; George G. C. Tseng, Reg. No. 41,355; Lester J. Vincent, Reg. No. 31,460; John Patrick Ward, Reg. No. 40,216; Stephen Warhola, P43,237; Charles T. J. Weigell, Reg. No. 43,398; Ben J. Yorks, Reg. No. 33,609; and Norman Zafman, Reg. No. 26,250; my attorneys; and Amy M. Armstrong, Reg. No. P42,265; Robert Andrew Diehl, Reg. No. P40,992; and Edwin A. Sloane, Reg. No. 34,728; my patent agents, with offices located at 12400 Wilshire Boulevard, 7th Floor, Los Angeles, California 90025, telephone (310) 207-3800, with full power of substitution and revocation, to prosecute this application and to transact all business in the Patent and Trademark Office connected herewith.

I hereby declare that all statements made herein of my own knowledge are true and that all statements made on information and belief are believed to be true; and further that these statements were made with the knowledge that willful false statements and the like so made are punishable by fine or imprisonment, or both, under Section 1001 of Title 18 of the United States Code and that such willful false statements may jeopardize the validity of the application or any patent issued thereon.

Full Name of First/Sole Inventor Wan-uk CHOI

Inventor's Signature *Wanuk Choi* Date Feb. 23, 1999

Residence Suwon-si, Kyungki-do, Korea Citizenship Korea
(City, State) (Country)

Post Office Address Kongwoo APT. 2-401, Younghwa-dong, Changan-ku, Suwon-si,
Kyungki- do, Korea


Full Name of Second/Joint Inventor : Kyou-yoon SHEEM

Inventor's Signature  Date Feb. 23, 1999

Residence Chonan-si, Chungchongnam-do, Korea Citizenship Korea
(City, State) (Country)

Post Office Address Keukdong APT. 111-1004, Doojung-dong, Chonan-si,
Chungchongnam-do, Korea

Full Name of Third/Joint Inventor Sang-young YOON

Inventor's Signature  Date Feb. 23, 1999

Residence Seoul, Korea Citizenship Korea
(City, State) (Country)

Post Office Address 722-3, Pongchon-dong, Kwanak-ku, Seoul, Korea

Full Name of Fourth/Joint Inventor _____

Inventor's Signature _____ Date _____

Residence _____ Citizenship _____
(City, State) (Country)

Post Office Address _____

Full Name of Fifth/Joint Inventor _____

Inventor's Signature _____ Date _____

Residence _____ Citizenship _____
(City, State) (Country)

Post Office Address _____

Full Name of Sixth/Joint Inventor _____

Inventor's Signature _____ Date _____

Residence _____ Citizenship _____
(City, State) (Country)

Post Office Address _____